

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
19 February 2004 (19.02.2004)

PCT

(10) International Publication Number  
WO 2004/015167 A2

(51) International Patent Classification<sup>7</sup>: C23C 18/12,  
B05D 1/20, 1/18, 5/12, 3/10, 1/00

[JP/JP]; c/o CANON KABUSHIKI KAISHA, 3-30-2,  
Shimomaruko, Ohta-ku, Tokyo 146-8501 (JP).

(21) International Application Number:  
PCT/JP2003/010215

(74) Agents: OKABE, Masao et al.; No. 602, Fuji Bldg., 2-3,  
Marunouchi 3-chome, Chiyoda-ku, Tokyo 100-0005 (JP).

(22) International Filing Date: 11 August 2003 (11.08.2003)

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,  
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,  
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,  
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
2002-233026 9 August 2002 (09.08.2002) JP  
2003-286820 5 August 2003 (05.08.2003) JP

(71) Applicant (*for all designated States except US*): CANON  
KABUSHIKI KAISHA [JP/JP]; 3-30-2, Shimomaruko,  
Ohta-ku, Tokyo 146-8501 (JP).


(84) Designated States (*regional*): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,  
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): OGAWA, Miki

[Continued on next page]

(54) Title: MESOSTRUCTURED FILM, POROUS FILM AND THE METHOD OF PREPARING THE SAME



(57) **Abstract:** It is an object of the present invention to provide a method for preparing mesostructured film having oriented channel structure and which is applicable to preparing mesostructured metal oxide. It is also an object of the present invention to provide meso porous film containing non-silica metal oxide in pore wall and having rod-like pores uniaxially aligned. It is further an object of the present invention to provide method for preparing mesostructured film including the steps of: preparing a reactant solution containing a precursor material for frame of mesostructured material which contains metal oxide, and an amphiphilic material; coating the substrate whose surface has alignment control ability with the reactant solution; and holding the substrate which has been coated with the reactant solution in a vapor-containing atmosphere.

WO 2004/015167 A2

**Published:**

— without international search report and to be republished upon receipt of that report

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*